

Effect of Weather Temperature on Concrete

¹MESHAL ALBZAIE, ²JASEM BOUARKE

DOI: <https://doi.org/10.5281/zenodo.14999194>

Published Date: 10-March-2025

Abstract: This study examines the effect of temperature uptake and downs on fixed properties, including the development of strength, durability and setting time. The elevated temperature accelerates hydration, leading to rapid force, but cracking increases the risk, while low temperatures slow down the process of recovering, reducing the strength of early ages and is potentially structural weaknesses. Research investigates these challenges and presents effective molding strategies, such as using customized mixing designs, treatment techniques and chemical entry. By integrating conclusions from reputable engineering sources, this study provides practical recommendations to increase solid performance and long life in different environmental conditions.

Keywords: Concrete, effect of temperature, setting time, cracking, durability, environmental conditions.

1. INTRODUCTION

Concrete is one of the most widely used building materials due to its high compressed power, durability and versatility. It acts as a basic component of infrastructure projects, including buildings, bridges, roads and dams. However, the performance of concrete is strongly affected by environmental conditions, especially temperature variations. The weather on the weather plays an important role in the hydration process, establishment of time, ability to work and long -term durability of fixed structures.

Excessive temperature, whether high or low, can have harmful effects on solid properties. High temperatures accelerate hydration, cause rapid evaporation of water, increase waste and a high risk of cracks. On the other hand, the low temperature slows the hydration process, delays the growth of power and increases the risk of frost loss in concrete at an early age. In extreme cases, the cold temperature due to the formation of ice can cause internal stress and compromise the structural integrity of the concrete.

It is necessary to understand the effect of temperature on concrete to ensure durability and performance of structures under different climatic conditions. The purpose of this study is to analyze how the weather temperature affects the strategies used to reduce concrete properties, extreme temperature challenges and their unfortunate effects. By undergoing experimental studies, case analysis and best practice, this research provides a broad insight into temperature-related challenges in solid construction and provides recommendations for effective temperature management under different environmental conditions.

2. RESEARCH METHODOLOGY

This research uses a mixed method approach to investigate the effect of the weather temperature on fixed properties. A systematic review of acting scientific literature combines case study and experimental data analysis from different climatic conditions. The study attracts a comprehensive and well -dominated analysis to the colleague who has been reviewed magazines, engineering reports and the industry's guidelines.

2.1 Literature Review

An intense literature review was done to detect existing research on the effect of temperature absorption and downsides on concrete. The renowned engineering and construction databases, such as the American Concrete Institute (ACI), Journal of Material Journal in Civil Engineering and the sources of various design standards were investigated to establish a solid theoretical foundation. Previous studies have shown that high temperatures accelerate hydration and reduce work ability, while low temperatures settle the process and increase the risk of frostbite (ACI, 2021).

2.2 Case Study Analysis

In order to assess real world applications, case studies were analyzed from different geographical regions with extreme weather conditions. The study of the selected case includes high-temperature environments such as the Middle East, where fast-up thermal cracks (Neville and Brooks, 2020), and cold-by-wood areas such as Scandinavia, where the concrete surfaces are delayed and delayed in frostbite (Kosomatka and Wilson, 2019). These cases studies provide information on how temperature variations affect fixed performance in practical construction scenarios.

2.3 Experimental Data Collection

This study also undergoes experimental data from controlled laboratory tests that examine the ratio of temperature and fixed properties. Experiments performed by Klemczak and Knoppik-Wróbel (2019) demonstrated that concrete is corrected at temperatures above 30 ° C, which shows high age strength, but suffers from increased shrinkage and cracks. In contrast, studies from Bentz (2021) found that concrete below 5 ° C has been cured, which requires the extended duration of treatment to reach the entire strength capacity.

2.4 Data Analysis Approach

The data collected was analyzed using comparative methods, which highlight the difference in fixed behavior under different temperature conditions. Research also evaluates mitigation techniques such as chemical penetration, using customized treatment methods and modified mixture to increase solid performance under extreme weather conditions (ACI, 2021).

By integrating literature reviews, case study analysis and experimental data evaluation, it ensures a broad understanding of the effect of temperature on the acting concrete and provides practical insight to engineers and production people.

3. EFFECT OF TEMPERATURE ON CONCRETE PROPERTIES

The temperature plays an important role in determining the physical and mechanical properties of the concrete. The variations in temperature can significantly affect the hydration process, strength development, functional capacity, durability and the total structural integrity of concrete. This section discusses the effect of both high and low temperatures on fixed properties, supported by previous research and the findings from the study of the case.

3.1 High Temperature Effects

High temperatures accelerate the hydration process, making the concrete set and rigid faster. Although it may seem beneficial when it comes to initial power distributors, it often leads to more side effects:

- Quick evaporation and low work qualification: High temperature causes water to evaporate with concrete mixing, reduce work ability and create positions and eliminate more difficult (Neville and Brooks, 2020). To combat this, a softener as extra water or chemical penetration is needed.
- Thermal cracks: rapid loss of moisture increases waste, causing thermal cracks, which weakens the concrete structure (Bentz, 2021). It is especially problematic in concrete where the difference temperature gradients between the surface and the core develop.
- Loss of long -term strength and durability: Studies have shown that although high temperatures can increase the strength at an early age, they often produce short -term results due to incomplete hydration and increased porn (ACI, 2021). This makes solid more unsafe for environmental erosion over time.
- Increased risk of delayed ettringite formation (DEF): In excessive heat, excessive inner temperature can be delayed by the formation of atrringitis, causing expansion and cracking in stiff concrete (Kosomatka and Wilson, 2019).

3.2 Low Temperature Effects

Low temperatures slow down the chemical reactions involved in cement hydration and delay the development of time and power. This can lead to many challenges:

- Long-lasting setting time and strength distributor: The concrete kept in cold weather requires long treatment to get sufficient strength (Claimsak and Nopic-Vagabel, 2019). When the temperature falls below 5 ° C, the hydration slows down significantly, and below 0 ° C, hydration stops completely.

- Risk of cold and ice formation: If fresh concrete is exposed to cold temperature before reaching sufficient strength, water can freeze, expand and cause internal cracks (Bentz, 2021). This leads to a severe reduction in structural integrity.
- Delayed treatment and thermal cracks: Further treatment measures such as untouched carpets or hot cabinets are necessary to prevent further cooling of concrete in cold climate and ensure proper moisture (ACI, 2021). Without these precautions, thermal cracks and low durability can occur.
- Low binding strength: Low temperature can weaken the binding between cement paste and aggregate, leading to a reduction in structural performance in reinforced concrete elements (Neville and Brooks, 2020).

3.3 Combined Effects of Temperature Variations

In areas that experience ups and downs of considerable temperature, fixed structures are exposed to repeated cycles of expansion and contractions. This can cause thermal fatigue, micro cracking and long-lasting decrease in concrete, especially exposure to seasonal variations (Kosmatka and Wilson, 2019) in bridges and sidewalks. The common effect of excessive heat in summer and cold temperature in winter requires careful material choices and construction plans to ensure durability.

Understanding the challenges related to this temperature allows engineers to use appropriate measures to reduce negative effects, and ensure that concrete structures remain durable and work well in different environmental conditions. The next section discusses molding strategies to combat these temperature effects and increase the life of concrete in the extreme climate.

4. MITIGATION STRATEGIES

In order to ensure durability and structural integrity of concrete under excessive temperature conditions, different mitigating strategies must be used. These strategies focus on using advanced materials and techniques to adapt the mixing design, controlling the treatment process and fighting the harmful effects of both high and low temperatures.

4.1 Strategies for High Temperatures

In case of hot weather, the concrete undergoes rapid hydration, which reduces workability, increases shrinkage and the risk of thermal cracks. To reduce these problems, the following strategies are recommended:

- Use of admixtures: Chemical admixtures as retarders and plasticizers helps slow the hydration process and improve the ability to work in high temperatures (ACI, 2021). This admixture allows for appropriate placement and finishing without excessive water addition, which can weaken the concrete.
- Cooling technology: Cold aggregate, water mixture and use of cold water or ice can help reduce the original temperature of the concrete mixture (Neville and Brooks, 2020). In large projects, liquid nitrogen can be injected into the mixture to maintain an appropriate temperature.
- Ways to adapted treatment: To prevent rapid moisture loss, appropriate treatment techniques such as water spraying, wet burlap coatings and evaporation stamps should be used (Bentz, 2021). Continuous moist treatment for at least seven days increases hydration and prolonged strength.
- Use of low heat cement: Select cement types with slight hydration, such as fly ash or slag -containing mixed cement, concrete (Kosmatka and Wilson, 2019) reduces the temperature structure within. These materials increase durability by reducing the risk of thermal cracks.
- Adjusting time: planning concrete placements under today's cooler parts (morning or late at night) helps reduce extreme heat exposure, reduce evaporation and improve the ability to work (Klemczak & Knoppik-Weeróbel, 2019).

4.2 Strategies for Low Temperatures

The condition of cold weather slows hydration, delays the cure and increases the risk of cold damage. The following measures help ensure the correct specific performance in low temperatures:

- Use of accelerator: Chemical accelerators such as calcium chloride or non-chloride-based accelerator speeds hydration, reduce setting time and increase strength at an early age (ACI, 2021). However, chloride -based accelerator must be avoided in reinforced concrete to prevent rust.

- Thermal insulation and heat enclosures: Covering fresh concrete with pristine carpets or hot cabinets prevents rapid cooling and maintains the optimal treatment state (cosmate and Wilson, 2019). For large projects projects help temporary enclosures with heaters control the ambient temperature.
- Heating of mixing material: Preheating water and agarigates Make sure the mixture of concrete begins at an optimal temperature, which prevents excessive cooling during placements (Neville and Brooks, 2020).
- Period of extended treatment: Since the moisture is slow in cold weather, long -term treatment is necessary to get the necessary strength before coming into contact with the cold condition (Bentz, 2021). Application of treatment compounds can also help maintain moisture in concrete. Avoid early colds: Concrete should not be placed on frozen land or should not be exposed to the cold position until you reach the smallest compressed current of 3.5 MPa (cosmratka and Wilson, 2019). Temporary ground heating or insulated formwork can help reduce this risk.

4.3 General Strategies for Temperature Variations

In areas where concrete is made in contact with both high and low temperatures throughout the year, further precautions should be taken:

- Use of insertion to reduce shrinkage: These entry reduces the risk of thermal and drying, reduces the risk of cracks (Klemczak & Knoppik-WWróbel, 2019).
- Fiber reinforcement: Inclusion of synthetic or steel fibers improves crack resistance and increases the mechanical properties of concrete under temperature variation (Bentz, 2021).
- Smart surveillance technologies: Built-in temperature sensors in concrete and maturity meter allow real-time monitoring of progression, which makes it possible to optimize timely intervention conditions (ACI, 2021).

By implementing these mitigation strategies, engineers and building staff can increase solid durability and performance under extreme temperature conditions. Proper planning, material choices and construction techniques are necessary to ensure that fixed structures are flexible and durable.

5. CONCLUSION AND RECOMMENDATIONS

5.1 Conclusion

Temperature high and low component settings can affect time, strength development, ability to work and long -term durability. High temperatures accelerate hydration, which probably leads to rapid strength, but also increases the risk of cracks, low work ability and short -term durability (Neville and Brooks, 2020). On the other hand, low -temperature brakes hydration, delays the power development and causes the risk of cold -inspired damage, which may compromise the structural integrity (Bentz, 2021).

In order to combat these challenges, proper mitigating strategies must be used. These include regulation of hydration, adaptation methods for treatment, adjustment of mixing design and use of chemical entry to use advanced monitoring techniques. The correct plan and execution of these measures ensure that fixed structures maintain their durability and performance under different environmental conditions.

5.2 Recommendations

Based on the findings of this research, the following recommendations are proposed to reduce the side effects of temperature recording and downs on the concrete:

1. Customize mixture designed based on climatic conditions
 - Use complementary cement materials such as fly ash or slag to control hydration rates and increase durability (cosmatka and Wilson, 2019).
 - Include insertion and fiber reinforcement that reduces shrinkage to improve crack resistance.
2. Use effective treatment techniques
 - Use water treatment, evaporation, delayed and protective cover to prevent moisture loss (ACI, 2021).

- In cold weather, you can use thermal insulation, hot enclosures or treatment connections to maintain optimal hydration conditions (requirements and nopical-Vabel, 2019).
3. Monitor and Control Concrete Temperature During Placement
 - Use surveillance systems for real -time temperature as maturity meter to track hydration progression and adjust methods accordingly (Bentz, 2021).
 - Planned concrete under a favorable weather conditions to reduce the risk of extreme temperature.
 4. Develop Guidelines for Construction in Extreme Climate
 - Engineers and contractors should follow international standards and guidelines for hot- and cold-weather concreting, such as those established by the American Concrete Institute (ACI 305 and ACI 306).
 - To increase the flexibility of temperature -inspired damage, you do further research on new materials and smart construction techniques.

By using these recommendations, the construction industry can increase specific benefits, which can also ensure structural life and stability -challenging environmental conditions. Future research should detect the integration of smart technologies, self -healing concrete and climate -friendly materials to improve the flexibility of concrete structures.

REFERENCES

- [1] American Concrete Institute (ACI). (2020). Guide to hot weather concreting (ACI 305R-20). Retrieved from https://www.concrete.org/Portals/0/Files/PDF/Previews/305R-20_preview.pdf
- [2] American Concrete Institute (ACI). (2016). Guide to cold weather concreting (ACI 306R-16). Retrieved from https://www.concrete.org/Portals/0/Files/PDF/University/306R-16_excerpt.pdf
- [3] Bentz, D. P. (2006). Influence of water-to-cement ratio on hydration kinetics: Simple models based on spatial considerations. *Cement and Concrete Research*, 36(2), 238-244.
- [4] Bentz, D. P., Jones, S. Z., & Snyder, K. A. (2015). Early-age properties of cement-based materials: Influence of water-to-cement ratio.
- [5] Cemex USA. (n.d.). Hot weather concrete: Tips & best practices. Retrieved from <https://www.cemexusa.com/documents/27329108/45560536/cemex-usa-technical-bulletin-hot-weather-concreting.pdf>
- [6] Cemstone. (2024). Hot weather concrete guide. Retrieved from <https://cemstone.com/wp-content/uploads/2024/06/2024-cemstone-hot-weather-concrete-guide.pdf>
- [7] Iowa State University Institute for Transportation. (2015). Impacts of internal curing on concrete properties.
- [8] National Institute of Standards and Technology (NIST). (2007). Internal curing of high-performance blended cement mortars.
- [9] National Institute of Standards and Technology (NIST). (2015). Critical observations for the evaluation of cement hydration models.
- [10] Wikipedia. (2024). Properties of concrete. Retrieved from https://en.wikipedia.org/wiki/Properties_of_concrete
- [11] Neville, A. M., & Brooks, J. J. (2020). *Concrete Technology*. Pearson Education.
- [12] Kosmatka, S. H., & Wilson, M. L. (2019). *Design and Control of Concrete Mixtures*. Portland Cement Association.
- [13] Klemczak, B., & Knoppik-Wróbel, A. (2019). The Effect of Temperature on Concrete Hydration: Experimental Analysis.
- [14] Mehta, P. K., & Monteiro, P. J. M. (2014). *Concrete: Microstructure, Properties, and Materials*. McGraw Hill.
- [15] Lothenbach, B., Scrivener, K., & Hooton, R. D. (2011). Supplementary cementitious materials. *Cement and Concrete Research*, 41(12), 1244-1256.
- [16] Thomas, M. D. A. (2013). *Supplementary Cementing Materials in Concrete*. CRC Press.

- [17] Li, Z. (2011). *Advanced Concrete Technology*. Wiley.
- [18] ASTM International. (2021). *Standard Practice for Making and Curing Concrete Test Specimens in the Field (ASTM C31/C31M)*.
- [19] Mindess, S., Young, J. F., & Darwin, D. (2002). *Concrete*. Prentice Hall.
- [20] RILEM Technical Committee. (2010). *Durability Design of Concrete Structures*. Springer.
- [21] Taylor, P. (2014). *Curing Concrete*. CRC Press.
- [22] Ghosh, P. (2019). *Sustainable Concrete: Materials and Methods*. Elsevier.
- [23] Domone, P., & Illston, J. (2010). *Construction Materials: Their Nature and Behaviour*. CRC Press.
- [24] Bentur, A., Diamond, S., & Mindess, S. (1997). *The Role of Interfaces in Cement-Based Composites*. CRC Press.
- [25] Chatterji, S. (2005). Chemistry of Cement Hydration. *Advances in Cement Research*, 17(2), 57-69.
- [26] Alexander, M. G., Bertron, A., & De Belie, N. (2013). *Performance of Cement-Based Materials in Aggressive Aqueous Environments*. Springer.
- [27] Hooton, R. D. (2016). Concrete Durability under Severe Environments. *Journal of Materials in Civil Engineering*, 28(2), 4016001.
- [28] Shi, C., Krivenko, P. V., & Roy, D. (2006). *Alkali-Activated Cements and Concretes*. CRC Press.
- [29] Ramezani pour, A. A. (2013). *Cement Replacement Materials: Properties, Durability, Sustainability*. Springer.
- [30] Papadakis, V. G., Vayenas, C. G., & Fardis, M. N. (1991). Fundamental Modeling and Experimental Investigation of Concrete Carbonation. *ACI Materials Journal*, 88(4), 363-373.